dentalCEtoday.com
Powered by Dentistry Today

Continuing Education

Course Number: 119

Achieving Excellence Using an Advanced Biomaterial: Part 2

Authored by Douglas A. Terry, DDS, Karl F. Leinfelder, DDS, MS, and Markus B. Blatz, DMD, PhD

Upon successful completion of this CE activity 2 CE credit hours may be awarded

A Peer-Reviewed CE Activity by DENTISTRY TODAY is an ADA CERP Recognized Provider

ADA C·E·R·P® Continuing Education Recognition Program
Dentistry Today is an ADA CERP Recognized Provider.

Academy of General Dentistry PACE Program Approval for Continuing Education
Approved PACE Program Provider
FAGD/MAGD Credit Approval
does not imply acceptance
by a state or provincial board of
dentistry or AGD endorsement.
June 1, 2009 to May 31, 2011
AGD Pace approval number: 309062

Opinions expressed by CE authors are their own and may not reflect those of *Dentistry Today*. Mention of specific product names does not infer endorsement by *Dentistry Today*. Information contained in CE articles and courses is not a substitute for sound clinical judgment and accepted standards of care. Participants are urged to contact their state dental boards for continuing education requirements.

Achieving Excellence Using an Advanced Biomaterial: Part 2

LEARNING OBJECTIVES:

After reading this article, the individual will learn:

- The 3 essential elements and fundamental principles for achieving clinical success with posterior composite resin restorations.
- An adhesive technique and protocol for the development of the Class I and Class V composite restoration.

ABOUT THE AUTHORS



Dr. Terry is a clinical assistant professor in the Department of Restorative Dentistry and Biomaterials, at the University of Texas Health Science Center Dental Branch at Houston. He is a member and the US vice president of International Oral Design. Dr. Terry is an editorial member of numerous peer-reviewed scientific journals and has published over 230 articles on various topics in aesthetic and restorative dentistry. He has authored the textbooks *Natural Aesthetics with Composite Resin and Aesthetic & Restorative Dentistry: Material Selection & Technique.* He has lectured internationally on various subjects in restorative and aesthetic dentistry. Dr. Terry is the founder and CEO of design Technique International and the Institute of Esthetic and Restorative Dentistry. He maintains a private practice in Houston, Tex. He can be reached at He can be reached at (281) 481-3483 or via e-mail at dterry@dentalinstitute.com.

Disclosure: Dr. Terry reports no conflict of interest.



Dr. Leinfelder is currently an adjunct professor at the University of North Carolina and professor emeritus at the University of Alabama. After 8 years on the faculty at Marquette, became the director of biomaterials clinical research in the Dental Research Center at the University of North Carolina, School of Dentistry. In 1983, he joined the School of Dentistry at the University of Alabama, held the Joseph Volker Chair, and also served as chairman of the Department of Biomaterials until 1994. He can be reached at (919) 370-9168 or kcullie@aol.com.

Disclosure: Dr. Leinfelder is an unpaid consultant for Pentron Clinical Technologies.



Dr. Blatz graduated and received an additional Doctorate as well as a postgraduate certificate in Prosthodontics from the University of Freiburg, Germany. He is currently a professor of Restorative Dentistry and Chairman of the Department of Preventive and Restorative Sciences at the University of Pennsylvania School of Dental Medicine. Dr. Blatz is a Diplomate of the German Society of Prosthodontics and Material Sciences. He is an editorial board member of numerous peer-reviewed scientific dental journals. He is a member of multiple professional organizations, including the European Academy of Esthetic Dentistry and OKU Honor Dental Society. Dr. Blatz has published and lectured extensively on various facets of restorative dentistry, implantology, and dental materials. He can be reached at (215) 573-3959 or via e-mail at mblatz@dental.upenn.edu.

Disclosure: Dr. Blatz receives research grants and support from Nobel Biocare, Straumann, Ivoclar Vivadent, Kurrary, Heraeus Kulzer, DENTSPLY, Coltène Whaledent, Noritake Dental Supply, and 3M ESPE.

This is part 2 of a 2-part article series. Part 1 of Dr. Terry, et al's article was published in the August 2009 issue of Dentistry Today (see article #116)

INTRODUCTION

The longevity of the composite restoration has been a topic of concern for many private practitioners, clinical studies, and research articles.[1-16] Early attempts to utilize composite resins in the posterior region of the mouth revealed complications, including: an elevated rate of occlusal wear, inadequate bonding systems, high

polymerization shrinkage and lack of adaptation to the margins after polymerization, and an increased incidence of microleakage with frequent secondary caries and postoperative sensitivity.[17-21] Improving serviceability of posterior composite resins in the oral cavity requires one to address these obstacles while developing an optimal protocol for placing these restorations.[22,23] A successful restorative procedure for posterior composite resins relies on the interrelation of 3 primary elements: restorative material selection, adhesion, and clinical technique (Figure 1). The fundamental principles of this process require maintaining sound tooth structure, achieving a sterile gap-free hybrid layer, and eliminating microleakage by securing a stress-free restorative-tooth interface.

This article discusses the primary elements and fundamental principles required for successful posterior composite resin restorations, and presents 2 clinical cases which demonstrate proper technique for placement of these restorations.

THE RESTORATIVE-TOOTH INTERFACE

The integrity of the bond and marginal adaptation to the tooth structure are critical for clinical success in composite restorations.[24] The restorative-tooth interface is constantly subjected to stress and strain imposed by polymerization shrinkage forces, thermal stimuli, and functional occlusal loads. These stresses may be the mechanism for the clinical challenges with adhesive restorations in clinical dentistry. These include microleakage, marginal breakdown, fractures, secondary caries, postoperative sensitivity, inadequate marginal adaptation, staining, and potential pulpal irritation.[25-28]

Before a restoration is even subjected to functional loads and thermal strains there is an initial interfacial stress developing during polymerization of the restorative materials and adhesion to tooth structure.[29] In a restorative technique using composite resins, the polymerization reaction of the resin matrix phase could compromise dimensional stability.[25] Therefore, a comprehensive understanding of the complex interplay between polymerization shrinkage and adhesion is necessary. This conversion of the monomer molecules into a polymer network is accompanied by a closer packing of the molecules, leading to bulk contraction.[30] Alternatively, when a curing material is bonded on all sides to rigid structures, bulk contraction cannot occur and shrinkage must be compensated for by increased stress, flexure, or gap formation at the adhesive interface.[25]

Polymerization shrinkage or curing contraction is the amount of volumetric decrease a composite system undergoes because of the curing process.[31] The cross-linking of resin monomers into polymers is responsible for an unconstrained volumetric shrinkage of 2% to 5%.[32] During the polymerization reaction, the visco-elastic behavior of the composite changes from viscous to viscous-elastic to elastic. While stress development is nonexistent in the viscous stage, in the visco-elastic stage stresses can partly be relieved by flow and elastic strain.[33]

The moment at which the material can no longer provide viscous flow to keep up with the curing contraction is referred to as the gel point.[25] When the composite material develops an elastic modulus, a volumetric polymerization contraction results in shrinkage stresses. The shrinkage stresses are transferred to the surrounding tooth structure because it restricts the volumetric changes.[33] The uncompensated forces may exceed the bond strength of the tooth-restoration interface, resulting in gap formation from a loss of adhesion.[34] The factors that influence polymerization shrinkage include: type of resin,[31] filler content of the composite,[31,35,36] elastic modulus of the material,[36] curing characteristics,[37] water sorption,[38-40] cavity configuration,[26] and the intensity of the light used to polymerize the composite.[33,41,42] By understanding this complex mechanism between polymerization shrinkage and adhesion, the clinician can select application techniques and restorative materials that prevent gap formation at the time of placement for each individual clinical situation.

In addition, the restorative interface is constantly subjected to functional loads after placement of the composite restoration. The cervical regions of the dentition may experience excessive eccentric loading from parafunctional habits such as clenching and bruxism.[43,44]

These repeated flexural forces can cause adhesive failure of cervical composite restorations at the dentin-resin interface which can result in microleakage, and/or partial or complete debonding of the restoration.[45] Interceptive occlusal equilibration and occlusal guard therapy prior to restorative treatment in conjunction with specific incremental placement techniques can provide restorative solutions.

THE PRIMARY RESTORATIVE ELEMENTS

The clinical success of composite restorations is determined by the interrelation of 3 essential elements: restorative material selection, adhesion, and technique. The proper integration of these 3 elements can result in an optimal restorative-tooth interface with improved clinical performance. However, an improper interrelation of these elements can lead to microleakage, gap formation, staining, sensitivity, and partial or complete debonding of the restoration that can result in long-term clinical failure (Figure 1).




Figure 1. A successful restorative procedure for posterior composite resins relies on the interrelation of 3 primary elements: restorative material selection, adhesion, and clinical technique.molar.

Restorative Material Selection

In the past, the physical and mechanical properties of the individual composite systems (ie, hybrid, microfill) had inherent limitations that confined their use to specific procedures. To achieve an optimal restorative result and compensate for these inequities required one to select and layer both a hybrid and a microfill resin system. These intricate layering techniques further complicated some clinicians' ability to achieve consistent and reliable results.

Newer formulations of nanohybrid composite resins have been designed with the concept of combining dentin color and enamel value in relationship to the natural tissue anatomy. These composite restorative systems not only simplify the replication of the optical properties of the natural tooth but have similar physical and mechanical properties to that of tooth structure. These advanced nanohybrid formulations provide composite resin with filler particle size that are dramatically smaller in size, can be dissolved in higher concentrations, can be polymerized into the resin system with molecules that can be designed to be compatible when coupled with a polymer, and provide unique characteristics (physical, mechanical, and optical). Further, optimizing the adhesion of restorative biomaterials to the mineralized hard tissues of the tooth is a decisive factor for enhancing the mechanical strength, marginal adaptation, and seal, while improving the reliability and longevity of the adhesive restoration.

In the past, the particle size of conventional composites was so dissimilar to the structural sizes of the hydroxyapatite crystal, dental tubule, and enamel rod, there was a potential for compromises in adhesion between the macroscopic (40 nm to 0.7 µm) restorative material and the nanoscopic (1 to 10 nanometers in size) tooth structure.[46] However, advanced resin technology has the potential to improve this continuity between the tooth structure and the nanosized filler particle and provide a more stable and natural interface between the mineralized hard tissues of the tooth and these restorative biomaterials. With the selection of these improved biomaterials, the clinician is able to preserve, conserve, and reinforce tooth structure with more conservative preparation designs.

Adhesion

The word "adhesion" is derived from the Latin roots that translate as "to" and "stick together." Defined as the "molecular attraction exerted between the surfaces of bodies in contact," the force

referred to as adhesion occurs when unlike molecules are attracted. Conversely, cohesion occurs when molecules of the same kind are attracted. The adhesive, frequently a viscous fluid, is comprised of a material or film that joins 2 substrates together and solidifies. The adherend is the material or initial substrate to which the adhesive is applied.[47]

In dentistry, a surface sealant would be defined as a single adhesive "joint," since only one interface exists. Adhesion or bonding is the process of forming an adhesive joint,[48] traditionally comprised of 2 substrates being joined so that the adhesive produces 2 interfaces which are part of the adhesive joint. While most adhesive joints involve only 2 interfaces, a bonded composite restoration would be an example of a more complex adhesive joint.[48] The physical and chemical properties of the adhesive are the most important factors in the performance of adhesive joints, since these are the properties that maintain the integral bond. Ensuring adequate performance of the adhesive joint requires knowledge and experience in the types of adherend (ie, enamel, dentin, metal alloy, composite material) and the nature of the surface pretreatment or primer. The adhesive, adherend, and surface all impact the durability of the bonded structure.

The mechanical behavior of the bonded structure is influenced by the details of the joint design and by the way in which the applied loads are transferred from one adherend to the other. The specific energy of adhesion defined by chemical, physical, and mechanical attributes of the substrate and adhesive determines the ability to form a joint and the resistance of the joint to failure.[48] Achievement of such interfacial molecular contact is a necessary first step in the formation of strong and stable adhesive joints. Inherent in the formation of an optimal adhesive bond is the ability of the adhesive to wet and spread on the adherends being joined. Good wetting usually occurs with solids that demonstrate high surface energy. Adhesives should exhibit low viscosities or low surface tension to increase their wetting capabilities.[49]

Once wetting is achieved, intrinsic adhesive forces are generated across the interface through mechanisms of mechanical interlocking, adsorption, diffusion, or any one of their combinations. Mechanical interlocking occurs when adhesive flows into pores in the adherend surface or around projections on the surface. In adsorption, adhesive molecules adsorb onto a solid surface and bond to it. This process may involve the chemical bonding between the resin (adhesive) and the inorganic or organic elements (adherend) of the tooth structure. Diffusion involves a mechanical or chemical bonding between polymer molecules (resin) and a precipitation of substances on the tooth surface (adherend). Most often, more than one of these mechanisms play a role in achieving the desired level of adhesion for various types of adhesive and adherend.[48]

The bonded restorative complex includes the outer layers of the substrate, the adhesive layer, and the restorative material. The integrity of the adhesive bonded interface is subject to failure arising from defects along the interface which can result in adhesive joint failure from debonding caused by crack formation and propagation. These defects at the interface come from trapped air voids, voids formed from solvent evaporation, areas of poor wetting, bubbles within the adhesive, curing shrinkage pores, areas of interfacial contamination, and excess moisture contamination.[48] A restorative material properly joined to the tooth substrate is able to provide the following: an improved marginal seal[50] while reducing marginal contraction gaps, microleakage, marginal staining, and caries; restoration retention from a durable interfacial adhesion between tooth and biomaterial[50]; a reduction of stress at the tooth-restorative interface[51]; biomechanical reinforcement of tooth structure; biological preservation of tissues; sealing of dentin tubules; and providing long-term functional success.[51-56]

A durable interfacial adhesion between the tooth and biomaterial requires a clean surface of the substrate, a low contact angle that allows the adhesive to spread over the entire surface of the substrate, and an optimal internal adaptation of the biomaterial to the substrate. This allows an intimate approximation of the material with the substrate without the entrapment of air pockets, which can result in adhesive failure. Further, the interface should have sufficient physical, chemical, and mechanical strength to resist stress from polymerization or occlusal forces, and a sufficient degree of cure of the adhesive.[47,48] Furthermore,

the clinician should have an understanding of the morphologic, histologic, and physiologic characteristics of the substrate (enamel and dentin) in order to achieve optimal adhesion.

Technique

In addition to enhancing the aesthetic result from multilayering of color, incremental layering techniques provide enhanced control of condensation of the individual increments of composite resin, densification, improved marginal adaptation and seal, thorough polymerization of the restorative material, and optimal bond formation. Further, these techniques allow control of overhangs in the lateral margins prior to curing, reduce the effects of polymerization shrinkage, allow the orientation of the curing light beam according to the position of each composite layer, and provide precise placement of optimal anatomical contours of the restoration.[57]

The margin quality and strength of a composite resin restoration is influenced by many factors which include: polymerization shrinkage, adhesion to the margins, cavity design and use of liners and bases, finishing and polishing techniques, viscosity and stiffness of the composite resin, flexibility of the cavity walls, position of increments of composite resin placement in cavity preparations, and the restorative application techniques.[27,34,58-61] A better understanding of these effects can influence the marginal integrity and strength of the composite restoration. Therefore, restorative techniques have been developed to reduce these effects, improve the marginal adaptation and seal,[61-65] and provide the clinician with maximum benefit for their application.[25] Numerous restorative techniques and innovations have been developed and proposed to overcome these shortcomings of deficient marginal adaptation, which include the following: light reflecting wedges,[66,67] wand position variation,[66,68] use of condensation and polymerization tips,[69-71] sandwich technique with self-cured composite, glass-ionomer cement or amalgam combined with the composite resin, and placement of glass inserts into pre-polymerized resin to reduce the volume of the shrinkage material.[69-72] Other techniques include reducing the volume of composite restorative material to allow better control of shrinkage,[73,74] incremental overlap and spot-cure methods,[66,75] and multilayering obturation methods.[62-65,76]

The positions of placement of the composite increments are described as vertical, horizontal, and oblique layering techniques. These techniques are the original multilayered methods and are used on small to large cavity preparations and are adequate for compensating for polymerization shrinkage. The multilayering techniques that the authors use include: horizontal layering, vertical layering, oblique layering, 3-sited, centripetal, direct-shrinkage, and successive cusp build-up. The selection of a particular incremental technique is determined by the type and dimension of the cavity preparation.

Knowledge and a desire to create are limited by the products clinicians have available to them for restorative procedures, and knowledge must be integrated with the proper selection of material and technique for each clinical situation. Maintaining the balance between restorative material selection, adhesion, and technique requires the skill and experience of the operator. The following procedures will illustrate the integration of these primary restorative elements to develop a stress-free tooth-restorative interface utilizing a low-shrinkage nanohybrid composite resin (KALORE [GC America]).

PREOPERATIVE RESTORATIVE CONSIDERATIONS

In the 2 clinical presentations of a Class I and Class V composite restoration the following considerations were completed before any restorative treatment was initiated. First, prior to administering anesthesia and dental dam isolation, the preoperative contact zone and excursive occlusal patterns were recorded and evaluated. This initial registration is valuable in the occlusal preparation design when determining placement of centric stops beyond or within the confines of the restoration and in minimizing finishing procedures.[77] In some clinical situations, it may be necessary to distribute the forces generated by the cusp over a larger surface area by recontouring the surface of the antagonistic cusp, thereby reducing the stress concentration at the interface. In addition, since anatomical form defines color, this occlusal evaluation can provide a

more accurate anatomical placement of the restorative material within the confines of the occlusal parameters.

Occlusal evaluation is also paramount for the long-term clinical success of the Class V adhesive restoration. In the restored tooth (ie, cervical restoration), lateral flexure resulting from eccentric forces produce tensile stresses at the marginal interface of the restoration, whereas heavy centric forces generate compressive stresses along the marginal interface of the cervical restoration. These repeated flexural forces can cause adhesive failure of cervical composite restorations at the dentin-resin interface which can result in microleakage, and/or partial or complete debonding of the restoration.[45] These occlusal considerations should be addressed at the treatment planning stage, prior to administering any restorative treatment. Intraoral elimination of interferences in the static and dynamic occlusion to achieve an ideal occlusion with maximal distribution of occlusal load should be performed only after splint therapy. Furthermore, interceptive occlusal equilibration should be initially performed on accurately mounted diagnostic models. Intraoral modifications in the occlusal pattern before any operative procedure is initiated can reduce cuspal flexure and cervical stresses that are capable of causing adhesive failure of cervical composite restorations. These preventative measures include equilibration with occlusal guard fabrication, coronoplasty, or orthodontic treatment.[78-81]

Next, the shade of the tooth should be determined before any restorative treatment is initiated. Shade selection should be accomplished prior to dental dam placement to prevent improper color matching as a result of dehydration and elevated values.[82] When teeth dehydrate, air replaces the water between the enamel rods, changing the refractive index, which makes the enamel appear opaque and white.[83] A preoperative selection of composite resins for the “artificial dentin” and “artificial enamel” shade and orientation was recorded using a custom-fabricated layered shade guide of polymerized composite resin. The shade tab is hand-layered with an opaque dentin layer and encased with a superficial layer of enamel corresponding to the specific shade. This shade matching technique using this system (2 Layer Shade System [Heraeus Kulzer]) provides excellent replication of dental composite color since it is synchronized with the same polymerized restorative material as the composite system which is being matched. This synchronization process allows the clinician to compare the actual polymerized restorative material of the composite system to the natural tooth color for a more accurate aesthetic color matching.

Upon request, the manufacturer provides the clinician with additional empty tabs that can be used to create individual patient shade tabs from the actual batch of restorative material the clinician is using for the restoration. The clear plastic shade tab provides a depth of restorative material from 1.5 mm to 1 mm in thickness. The advantages of the custom shade guide include the following: provides a full range of natural colors; variability between shade guides can be minimized; the actual polymerized restorative material is used in fabricating the restoration; any technique sensitivity affecting the parameters of color can be incorporated into the custom shade tabs; tabs can be fabricated to conform to specific space limitations for opacious dentin and enamel layer; characterizations at any depth in the restoration may be placed and described in terms of the color parameters and a more accurate representation and design of the anatomical surface morphology such as macro and micro morphological characteristics; provides a more accurate shade guide, an efficient verification of color, ease of correction (increasing or decreasing hue, chroma, and value), and communication for laboratory processed composites; compensates for adjustment to lot variations of composite resin materials; and provides for color combinations.[84-86]

THE OCCLUSAL LESION RESTORED WITH A CLASS I COMPOSITE RESTORATION

Case Report

A 21-year-old patient presented with initial carious lesions in the occlusal fissures surrounding the pre-existing sealant on the mandibular right first molar (Figure 2). Clinical evaluation and consultation revealed numerous other incipient carious lesions in posterior teeth of different quadrants that were the result of a recent change in dietary pattern with an increased consumption of carbonated beverages containing sugar. The predisposing environment

was altered by cessation of the habit and introduction of 1.1% neutral sodium home fluoride treatments (Fluoridex [Discus Dental]).

Prior to administering anesthesia and dental dam isolation, the preoperative occlusal stops and excursive guiding planes were recorded with articulation paper and were transferred to a hand drawn occlusal diagram, recorded on an intraoral or digital camera and/or indicated and reviewed on a stone model. A preoperative selection of composite resins with their shade and orientation was recorded (Figure 3). The use of a color corrected daylight source of 5,500 K (Rite•Lite Shade Matching Lite [AdDent]) was used for proper color registration.

The cavity configuration (C-factor) has a significant influence on the magnitude of the shrinkage stresses generated from polymerization shrinkage. The C-factor is defined as the ratio between the free and bonded restoration surfaces.[26] The Class I cavity has the highest C-factor (ie, Class I-5/1, Class II-4/2) and the greatest internal stress. The following clinical presentation focuses on managing and minimizing these stresses by utilizing a combination of stress-reduction techniques.

Once anesthesia was administered, the treatment site was isolated with a dental dam to achieve adequate field control and protect against contamination.[87,88] Quantitative light-induced fluorescence (DIAGNOdent [KaVo]) was used in conjunction with radiographic findings to aid in the detection and identification of the irreversible infected carious tissue on the mandibular right first molar and served as a guide for its removal.[89,90] The carious dentin was removed with a slow-speed carbide round bur (No. 4 [Midwest Dental]) and spoon excavators, and reexamined for caries with quantitative light-induced fluorescence. The preparation was designed so as to remove the carious process. Removal of healthy tooth structure should be carried out only when the occlusal outline requires extension beyond or within the functional stops. The width of the preparation should be as narrow as possible, since the wear resistance of the restoration is a direct function of dimension.[91] The occlusal margins of the preparation generally should not be beveled. Beveling automatically increases the width of the preparation, which in turn increases the potential for including the centric holding areas. This in turn increases the potential for increasing wear of the restoration.



Figure 2. Preoperative occlusal view reveals caries in the fissures surrounding a pre-existing sealant on the mandibular right first molar.



Figure 3. Shade determination was performed before dental dam placement with a custom fabricated composite shade tab.

One restorative technique for reducing shrinkage stress at the interface involves utilizing resin modified glass-ionomer as a cavity base. By reducing the volume of composite resin material the shrinkage stress is minimized. A polyacrylic acid solution (Cavity Conditioner [GC America]) was applied to the dentin surface for 10 seconds, rinsed with water, and lightly air-dried. A radiopaque glass-ionomer (Fuji IX GP [GC America]) was injected and condensed with a ball-tipped instrument (M-1 [American Eagle Instruments]). After 2 minutes and 30 seconds, the cavity walls were finished with a fine diamond under-water spray. The preparation was scrubbed with a 2% chlorhexidine solution (Consepsis [Ultradent Products]), rinsed, and lightly air-dried. The "total etch" technique was used to minimize the potential of microleakage and enhance bond strength to dentin and enamel.[92-94] The preparation was etched for 15 seconds with 32% phosphoric acid (Uni-Etch with BAC [BISCO]), rinsed for 5 seconds, and gently air-dried for 5 seconds (Figure 4). A single-component adhesive (Adper Single Bond Plus [3M ESPE]) was applied with a disposable applicator for 20 seconds with a continuous motion, reapplying every 5 seconds (Figure 5). Any excess was removed with the applicator, and the adhesive agent was light-cured for 30 seconds. Although a small amount of excess adhesive can

be applied over the margins to improve sealing, this excess should be removed during finishing procedures.

The cavity preparation was filled incrementally, utilizing an A-1 shaded hybrid composite (KALORE) from the preoperative shade selection (Figure 6). Each increment was gently condensed with a clean, nonsticking ball-tipped instrument (M-1) to ensure complete adaptation to the underlying resin and tooth structure (Figure 7). Each increment was light-cured for 40 seconds using a ramp curing mode. Using low-intensity curing light sequences to reduce shrinkage stress controls the plasticity (flow capacity) of the restoration during curing, while the final mechanical stability of the restoration remains unaffected.[33,42] When composites are polymerized with high-curing light intensities, larger gaps between the cavity walls and the restorative material are created than are found with the use of low-intensity lights. Considerable stress reduction occurs during the first 10 seconds of light activation.[33] Employing a lower-intensity light power during the first 20 seconds extends the visco-elastic stage of setting—an interval in which stress can be partly relieved by flow and elastic strain.[95] Since the rate of conversion determines the rate of shrinkage stress development, a moderation of the reaction may result in an overall stress reduction by allowing more yielding of the free surface of the restoration to the underlying contracting bulk, as a result of a slower stiffness development.[33] This initial reduced conversion rate of the resin material results in a higher degree of marginal adaptation at the interface of the cavity and restoration,[42] causing less damage at this interface.[25,33,41,42,96,97]

Furthermore, to reduce the possibility of cuspal flexure, a composite hybrid (KALORE) with a low volumetric polymerization shrinkage was selected.[98] Additionally, this problem may be reduced by a diagonal layering of the hybrid in increments of 1 mm and feathering the material up the cavity wall in a "V" shape[99,100] (Figure 8). Opposing enamel walls should not be contacted by the same increment[101]; this will minimize the wall-to-wall shrinkage and thus reduce intercuspal stress.[102] The application of the composite in oblique layers results in fewer contraction gaps at the margins. Continue to condense and shape the composite resin to correspond to cusp development and dentin replacement (Figure 9). It is important to anticipate the final result and not trespass in the final artificial enamel zone, and allow space for the overlying translucent enamel shade.




Figure 4. After the carious dentin was removed with a minimal preparation design, the preparation was etched for 15 seconds with 32% phosphoric acid (Uni-Etch with BAC [Bisco]) rinsed for 5 seconds, and gently air-dried.




Figure 5. A single component adhesive (Adper Single Bond Plus [3M ESPE]) was applied for 20 seconds to the entire preparation, air-thinned and light-cured.




Figure 6. An increment of A-1 shaded hybrid composite (KALORE [GC America]) was placed with a long-bladed interproximal instrument to the cavity wall and light cured for 40 seconds.




Figure 7. Using an oblique layering technique, successive increments of A-1 shaded hybrid composite (KALORE) were adapted to the cavity wall with a ball-tipped instrument (M-1 [American Eagle Instruments]).

Once the artificial dentin layer was developed a final

artificial enamel layer, a natural translucent shaded nanohybrid (KALORE), was placed and contoured with a long bladed instrument (TNCVIPCL, Hu-Friedy) to an ideal functional and anatomical occlusal morphology, and polymerized for 40 seconds (Figure 10). A thin layer of glycerin was applied to the surface and polymerized for a 2-minute post-cure, ensuring complete polymerization of the composite resin at the margins.

Developing the restoration in increments and considering the occlusal morphology and occlusal stops allows the clinician to minimize finishing procedures[77] and results in a restoration with improved physical and mechanical characteristics and less potential for microfracture. At least one study has revealed that a reduction in finishing results in less damage to the composite, as well as improved wear and clinical performance.[100] However, a proper meticulous finishing protocol can also increase the longevity of the restoration,[103,104] since a smooth surface can reduce plaque retention, thus minimizing the potential for gingival inflammation, surface staining, and secondary caries.[105-107]

The occlusal refinement was achieved with a No. 30 fluted pyramidal-shaped finishing bur (H274 [Brasseler USA]), closely observing the tooth-resin interface and using a dry protocol. After the initial finishing procedure, the margins and surface defects were sealed. All accessible margins were etched with a 37.5% phosphoric acid, rinsed, and dried. A composite surface sealant was applied and cured to seal any cracks or microscopic porosities that may have formed during the finishing procedures. The use of a surface sealant has been shown to reduce the wear rate of posterior composite resin restorations.[108] The final polish was accomplished with prepolish and high shine silicone rubber points (Diacomp [Brasseler USA]) and polishing cups (Enhance Polishing Cups [DENTSPLY Caulk]) with a synthetic diamond polishing paste (Diamond Paste, Leach and Dillon).

The dental dam was removed and the patient was asked to perform closure without force, and then centric, protrusive, and lateral excursions. Any necessary equilibration was accomplished with No. 12 and No. 30 pyramidal-shaped finishing burs (H274) and the final polish was repeated. The contact was tested with unwaxed floss to ensure the absence of sealant in the contact zone and the margins inspected. The clinical postoperative result achieved through the use of direct composite resin reflects the harmonious integration of color with anatomical form and function while enhancing marginal integrity and wear resistance (Figure 11).




Figure 8. The oblique layering technique reduces the ratio of cavity volume to area of the cavity walls which results in a substantial reduction in the marginal contraction gap.




Figure 9. The artificial dentin core was developed in relationship to the anatomical morphology, while preserving an adequate dimension for the artificial enamel layer.




Figure 10. The artificial enamel layer, a natural translucent shaded nanohybrid composite (KALORE) was applied over the dentin core with a long-bladed instrument to the ideal anatomical contours and light-cured for 40 seconds.

THE CERVICAL LESION RESTORED WITH A CLASS V COMPOSITE RESTORATION

Case Report

The patient, a 42-year-old male, presented with sensitivity of the maxillary right premolars. Clinical examination revealed irregular V- or wedged-shaped cervical defects with no caries, plaque, or gingival inflammation (Figure 12). Wear patterns were present on the occlusal surfaces of these teeth. After review of the patient's medical and dental history and considering all the

activities and effects from the loss of tooth substance, a differential diagnosis indicated multifactorial abrasive-abfraction lesions[109] caused from tensile stresses and toothbrush abrasion.

Upon successful stabilization with occlusal splint therapy and a careful mock equilibration on accurately mounted diagnostic models, an occlusal equilibration was performed to eliminate interferences in the static and dynamic occlusion and provide maximal distribution of occlusal load.[81] A preoperative selection of composite resins with shade and orientation was recorded and photographed (Figure 13).

The Class V "erosion" lesion continues to present an aesthetic and functional dilemma to the restorative dentist. As shown, the abfraction lesion is a noncarious lesion caused from deflective occlusal contacts. The teeth bend and the stresses at the cervix of the tooth cause a loss of tooth structure. To complicate matters, many of these patients present because of sensitivity to brushing and temperature changes, and may require anesthesia. Once anesthesia had been administered, the teeth were isolated with a dental dam to achieve adequate field control and to protect against contamination.[87,88] A modified technique was used to create an elongated opening that allowed placement of the dam over the retainer.[110] A nonmedicated retraction cord was placed since the lesion was located below the free gingival margin. This provides improved access and reduces the potential for crevicular fluid contamination (Figure 14). A bevel was placed on all margins that were in enamel to prevent microleakage however, a butt joint should be prepared if the gingival margin is in cementum/dentin. To improve the aesthetic results, a long bevel was placed on the coronal margin. Although mechanical retention is not required for successful adhesion, groove placement can also provide resistance to the internal and external components of stress-polymerization shrinkage and tooth flexure.[111] In clinical situations where there is sclerotic dentin, a slow speed bur or air abrasion may be used to roughen the dentin surface to allow better resin penetration through the sclerotic dentin and into the tubules.[94]

For patients with extreme tooth sensitivity, a specific tooth conditioning procedure can be employed to reduce



Figure 11. The postoperative result reveals a natural integration of composite resin with tooth structure.



Figure 12. Preoperative facial view of wedge-shaped cervical lesions on the maxillary right premolars.



Figure 13. Development of a custom shade tab of the exact restorative material (KALORE) allows a more accurate and realistic representation of the natural tooth structure.



Figure 14. A retraction cord was placed to gain adequate access to the gingival margin and to allow moisture control during the adhesive procedure.

technique sensitivity and the potential for microleakage, while increasing the potential for enamel bonding. This procedure involves combining adhesive strategies, ie, use of a self-etch adhesive with the dentin and total-etch adhesive with enamel. Since self-etching adhesives do not require rinsing and drying, technique sensitivity often associated with dehydration and rehydration of dentin in the total-etch (or etch-and-rinse) technique is eliminated. In comparison to total-etch adhesives, self-etch adhesives do not allow a discrepancy between the depth of demineralization and depth of resin infiltration because both processes occur simultaneously.[112] Further, since the smear plugs are not removed before the application of the self-etch adhesive, the potential for postoperative sensitivity is less than with total-etch adhesives.[112] Finally, by only allowing phosphoric acid etching of the enamel substrate, the bonding potential at the restorative-tooth interface may be improved.

The preparations were scrubbed with a slurry mixture of disinfectant and pumice. A self-etch adhesive (G-Bond [GC America]) was placed on the dentin surface using a No. 0 sable brush, allowed to dwell for 10 seconds, dried for 5 seconds, and light-cured for 10 seconds (Figures 15a and 15b). An A-2-shaded flowable composite (Gradia Direct Flo [GC America]) was placed over the entire dentin surface with a No. 0 sable brush and light cured for 40 seconds (Figure 16). The remaining preparation (ie, composite and enamel) was etched for 15 seconds with a 35% orthophosphoric acid (Gluma Etch 35 Gel [Heraeus Kulzer]), rinsed for 5 seconds, and gently air-dried for 5 seconds. This technique minimizes the potential of microleakage and enhances the bond strength to enamel.[92-94] A single component adhesive (Adper Single Bond Plus) was





Figure 15a and 15b. A self-etch adhesive was placed on the dentin surface, using a No. 0 sable brush **(15a)**; and allowed to dwell for 10 seconds, dried for 5 seconds and light-cured for 10 seconds **(15b)**.



Figure 16. A small amount of A-2 shaded flowable composite (Gradia, GC America) was applied to the axial wall and uniformly distributed over the dentin surface.



Figure 17. After acid etching the remaining preparation, an adhesive was applied, air-thinned, and light-cured for 20 seconds.

applied with a disposable applicator for 20 seconds using a light continuous scrubbing motion (Figure 17). The adhesive was gently air-dried for 5 seconds and light-cured for 20 seconds.

An artificial dentin layer of A-1 shaded nanohybrid composite resin (KALORE) was applied and adapted with a long-bladed interproximal instrument and light-cured for 40 seconds (Figures 18a and 18b) An artificial enamel layer, a clear translucent shaded nanohybrid composite (KALORE), was placed with a long-bladed interproximal instrument and contoured to the proper emergence profile with a No. 2 sable brush, and light-cured for 40 seconds (Figure 19).

Shaping and contouring was performed with a series of finishing burs, dry, in order to replicate natural form and texture. Dry finishing allows for better visualization of the contour and margins. It is important not to overheat the resin by using excessive pressure. Also, it is imperative not to ditch or scar the cementum at the gingival margin. The gingival tissue was retracted and protected during finishing using a gingival protector (Zekrya Gingival Protector [DMG America]) (Figure 20). Any excess resin can be removed with a No. 12 scalpel and the retraction cord removed to inspect for overhangs.

The restorations and all margins were re-etched for 15 seconds and rinsed for 5 seconds, and a layer of composite surface sealant (OptiGuard [Kerr]) was applied over the margins and the restoration. This will prevent leakage and seal any microfractures in the material caused from the finishing procedures. To increase the smoothness of the restorations, polishing was completed with prepolish and high shine silicone cups, points, and a synthetic foam cup with diamond polishing paste (Figures 21a and 21b). The






Figure 18a and 18b. The artificial dentin layer, an A-1 shaded nanohybrid composite (KALORE) was applied with a long bladed composite instrument **(18a)**; and light-cured for 40 seconds **(18b)**.



Figure 19. An artificial enamel layer, a clear translucent shaded nanohybrid composite (KALORE) was applied with an interproximal instrument, adapted, and smoothed with a No. 2 sable brush.



Figure 20. The cervical region was contoured and finished using a 30-fluted short tapered finishing bur (ET-3 [Brasseler USA]).

completed restorations reinstated a harmonious integration with the surrounding tissues while eliminating excessive eccentric forces and cervical sensitivity for the patient (Figure 22).




Figure 21. Polishing of the facial surface was completed with rubber cups as well as diamond polishing paste and a foam cup.

CONCLUSION

Securing and maintaining a stress-free restorative-tooth interface defines restorative success. The restorative process requires an integration of 3 primary elements of restorative dentistry: restorative material selection, adhesion, and technique. The restorative dentist must have knowledge of the physical properties of these restorative materials and their application in a variety of adhesive procedures in prosthodontics and restorative dentistry in order to make a proper selection. However, studies indicate that the accuracy of a procedure may be controlled more by the technique than the material.[113] Thus, this knowledge must be integrated with the proper technique for each specific clinical situation. Consequently, the ultimate success of the final restoration depends on the skill of the operator and the experience acquired with a given technique. Therefore, since clinical success begins and ends with dimensional stability at the interface, a balance between these primary restorative elements can improve the long-term clinical success for posterior composite resins.



Figure 22. The postoperative view reflects an ideal integration of composite, tooth structure, and soft tissue at the restorative interface.

(For more information see *Aesthetic & Restorative Dentistry: Material Selection & Technique* at everestpublishingmedia.net and quintpub.com.)

REFERENCES

1. Hickel R, Manhart J, García-Godoy F. Clinical results and new developments of direct posterior restorations. *Am J Dent*. 2000;13:41D-54D.
2. Hickel R, Manhart J. Longevity of restorations in posterior teeth and reasons for failure. *J Adhes Dent*. 2001;3:45-64.
3. Bernardo M, Luis H, Martin MD, et al. Survival and reasons for failure of amalgam versus composite posterior restorations placed in a randomized clinical trial. *J Am Dent Assoc*. 2007;138:775-783.
4. Manhart J, Chen H, Hamm G, et al. Buonocore Memorial Lecture. Review of the clinical survival of direct and indirect restorations in posterior teeth of the permanent dentition. *Oper Dent*. 2004;29:481-508.
5. Opdam NJ, Bronkhorst EM, Roeters JM, et al. A retrospective clinical study on longevity of posterior composite and amalgam restorations. *Dent Mater*. 2007;23:2-8.
6. Poyser NJ, Briggs PF, Chana HS, et al. The evaluation of direct composite restorations for the worn mandibular anterior dentition—clinical performance and patient satisfaction. *J Oral Rehabil*. 2007;34:361-3767.
7. Brunthaler A, König F, Lucas T, et al. Longevity of direct resin composite restorations in posterior teeth. *Clin Oral Investig*. 2003;7:63-70.
8. Hondrum SO. The longevity of resin-based composite restorations in posterior teeth. *Gen Dent*. 2000;48:398-404.
9. van Dijken JW. Direct resin composite inlays/onlays: an 11 year follow-up. *J Dent*. 2000;28:299-306.
10. Gaengler P, Hoyer I, Montag R. Clinical evaluation of posterior composite restorations: the 10-year report. *J Adhes Dent*. 2001;3:185-194.
11. van Noort R, Davis LG. A prospective study of the survival of chemically activated anterior resin composite restorations in general dental practice: 5-year results. *J Dent*. 1993;21:209-215.
12. Smales RJ, Gerke DC. Clinical evaluation of four anterior composite resins over five years. *Dent Mater*. 1992;8:246-251.
13. Lundin SA. Studies on posterior composite resins with special reference to class II restorations. *Swed Dent J Suppl*. 1990;73:1-41.
14. Lundin SA, Koch G. Class I and II composite resin restorations: 4-year clinical follow up. *Swed Dent J*. 1989;13:217-227.
15. Geurtsen W, Schoeler U. A 4-year retrospective clinical study of Class I and Class II composite restorations. *J Dent*. 1997;25:229-232.
16. Rowe AH. A five year study of the clinical performance of a posterior composite resin restorative material. *J Dent*. 1989;17(suppl 1):S6-9, discussion S26-28.
17. Eames WB, Strain JD, Weitman RT, et al. Clinical comparison of composite, amalgam, and silicate restorations. *J Am Dent Assoc*. 1974;89:1111-1117.
18. Feinman, RA. The plunging ball technique: Class II direct composite resins. *Pract Periodontics Aesthet Dent*. 1992;4:43-48.
19. Hornbrook DS. Optimizing form and function with the direct posterior composite resin: a case report. *Pract Periodontics Aesthet Dent*. 1996;8:405-411.
20. Lacy AM. A critical look at posterior composite restorations. *J Am Dent Assoc*. 1987;114:357-362.
21. Lyons K. Alternatives to amalgam. *N Z Dent J*. 1997;93:47-50.
22. Bichacho N. The centripetal build-up for composite resin posterior restorations. *Pract Periodontics Aesthet Dent*. 1994;6:17-23.
23. Bayne SC, Heymann HO, Sturdevant JR, et al. Contributing co-variables in clinical trials. *Am J Dent*. 1991;4:247-250.
24. Bouschlicher MR, Cobb DS, Boyer DB. Radiopacity of compomers, flowable and conventional resin composites for posterior restorations. *Oper Dent*. 1999;24:20-25.
25. Davidson CL, Feilzer AJ. Polymerization shrinkage and polymerization shrinkage stress in polymer-based restoratives. *J Dent*. 1997;25:435-440.
26. Feilzer AJ, de Gee AJ, Davidson CL. Setting stress in composite resin in relation to configuration of the restoration. *J Dent Res*. 1987;66:1636-1639.
27. Kemp-Scholte CM, Davidson CL. Marginal sealing of curing contraction gaps in Class V composite resin restorations. *J Dent Res*. 1988;67:841-845.
28. Bausch JR, de Lange K, Davidson CL, et al. Clinical significance of polymerization shrinkage of composite resins. *J Prosthet Dent*. 1982;48:59-67.
29. Labella R, Lambrechts P, Van Meerbeek B, et al. Polymerization shrinkage and elasticity of flowable composites and filled adhesives. *Dent Mater*. 1999;15:128-137.
30. Loshak S, Fox TG. Cross-linked polymers. I. Factors influencing the efficiency of cross-linking in copolymers of methyl methacrylates and glycol methacrylates. *J Amer Chem Soc*. 1953;75:3544-3550.
31. Quellet D. Considerations and techniques for multiple bulk-fill direct posterior composites. *Compend Contin Educ Dent*. 1995;16:1212-1226.
32. Ferracane JL. Using posterior composites appropriately. *J Am Dent Assoc*. 1992;123:53-58.
33. Feilzer AJ, Dooren LH, de Gee AJ, et al. Influence of light intensity on polymerization shrinkage and integrity of restoration-cavity interface. *Eur J Oral Sci*. 1995;103:322-326.
34. Davidson CL, de Gee AJ, Feilzer A. The competition between the composite-dentin bond strength and the polymerization contraction stress. *J Dent Res*. 1984;63:1396-1399.
35. Munksgaard EC, Hansen EK, Kato H. Wall-to-wall polymerization contraction of composite resins versus filler content. *Scand J Dent Res*. 1987;95:526-531.
36. Iga M, Takeshige F, Ui T, et al. The relationship between polymerization shrinkage measured by a modified dilatometer and the inorganic filler content in light cured composites. *Dent Mater J*. 1991;10:38-45.
37. Krejci I, Lutz F. Marginal adaptation of Class V restorations using different restorative techniques. *J Dent*. 1991;19:24-32.
38. Alster D, Feilzer AJ, de Gee AJ, et al. The dependence of shrinkage stress reduction on porosity concentration in thin resin layers. *J Dent Res*. 1992;71:1619-1622.
39. Fan PL, Edahl A, Leung RL, et al. Alternative interpretations of water sorption values of composite resins. *J Dent Res*. 1985;64:78-80.
40. Soltesz U, Bath P, Klaiber B. Dimensional behavior of dental composites due to polymerization shrinkage and water sorption. In: Christel P, Meunier A, Lee AJC, eds. *Biological and Biomechanical Performance of Biomaterials: Proceedings of the Fifth European Conference on Biomaterials, Paris, France, September 4-6, 1985*. Amsterdam: Elsevier; 1986.
41. Unterbrink GL, Muessner R. Influence of light intensity on two restorative systems. *J Dent*. 1995;23:183-189.
42. Uno S, Asmussen E. Marginal adaptation of a restorative resin polmerized at reduced rate. *Scand J Dent Res*. 1991;99:440-444.
43. Grippo JO. Abfractions: a new classification of hard tissue lesions of teeth. *J Esthet Dent*. 1991;3:14-19.
44. Heymann HO, Sturdevant JR, Brunson WD, et al. Twelve-month clinical study of dentinal adhesives in class V cervical lesions. *J Am Dent Assoc*. 1988;116:179-183.

45. Lee WC, Eakle WS. Possible role of tensile stress in the etiology of cervical erosive lesions of teeth. *J Prosthet Dent*. 1984;52:374-380.
46. Muselmann M. Composites make large difference in "small" medical, dental applications. *Composites Technology*. 2003;6:24-27.
47. Anusavice KJ. Structure of matter and principles of adhesion. In: *Phillips' Science of Dental Materials*. 10th ed. Philadelphia, Pa: WB Saunders; 1996.
48. Craig RG, Powers JM. *Restorative Dental Materials*. 11th ed. St. Louis, Mo: Mosby; 2002.
49. Touati B, Miara P, Nathanson D. *Esthetic Dentistry & Ceramic Restorations*. London, England: Martin Dunitz; 1999.
50. Armstrong SR, Boyer DB, Keller JC. Microtensile bond strength testing and failure analysis of two dentin adhesives. *Dent Mater*. 1998;14:44-50.
51. Goracci G, Mori G. Esthetic and functional reproduction of occlusal morphology with composite resins. *Compend Contin Educ Dent*. 1999;20:643-648.
52. Barkmeier WW, Cooley RL. Laboratory evaluation of adhesive systems. *Oper Dent*. 1992;5(suppl):50-61.
53. Touati B. Bonded ceramic restorations: achieving predictability. *Pract Periodontics Aesthet Dent*. 1995;7:33-37.
54. Santos J, Bianchi J. Restoration of severely damaged teeth with resin bonding systems: case reports. *Quintessence Int*. 1991;22:611-615.
55. Van Meerbeek B, Vanherle G, Lambrechts P, et al. Dentin- and enamel-bonding agents. *Curr Opin Dent*. 1992;2:117-127.
56. Eakle WS. Fracture resistance of teeth restored with class II bonded composite resin. *J Dent Res*. 1986;65:149-153.
57. Kovarik RE, Ergle JW. Fracture toughness of posterior composite resins fabricated by incremental layering. *J Prosthet Dent*. 1993;69:557-560.
58. Roulet JF, Noack MJ. Criteria for substituting amalgam with composite resins. *Int Dent J*. 1991;41:195-205.
59. McCoy RB, Anderson MH, Lepe X, et al. Clinical success of class V composite resin restorations without mechanical retention. *J Am Dent Assoc*. 1998;129:593-599.
60. Carvalho RM, Pereira JC, Yoshiyama M, et al. A review of polymerization contraction: the influence of stress development versus stress relief. *Oper Dent*. 1996;21:17-24.
61. Dietschi D, De Siebenthal G, Neveu-Rosenstand L, et al. Influence of the restorative technique and new adhesives on the dentin marginal seal and adaptation of resin composite Class II restorations: an in vitro evaluation. *Quintessence Int*. 1995;26:717-727.
62. Eick JD, Welch FH. Polymerization shrinkage of posterior composite resins and its possible influence on postoperative sensitivity. *Quintessence Int*. 1986;17:103-111.
63. Lutz F, Kull M. The development of a posterior tooth composite system in vitro investigation. *SSO Schweiz Monatsschr Zahnheilkd*. 1980;90:455-483.
64. Koenigsberg S, Fuks A, Grajower R. The effect of three filling techniques on marginal leakage around Class II composite resin restorations in vitro. *Quintessence Int*. 1989;20:117-121.
65. Tjan AH, Bergh BH, Lidner C. Effect of various incremental techniques on the marginal adaptation of class II composite resin restorations. *J Prosthet Dent*. 1992;67:62-66.
66. Kays BT, Sneed WD, Nuckles DB. Microhardness of Class II composite resin restorations with different matrices and light positions. *J Prosthet Dent*. 1991;65:487-490.
67. Lutz F, Krejci I, Luescher B, et al. Improved proximal margin adaptation of Class II composite resin restorations by use of light-reflecting wedges. *Quintessence Int*. 1986;17:659-664.
68. Kelsey WP III, Shearer GO, Cavel WT, et al. The effects of wand positioning on the polymerization of composite resin. *J Am Dent Assoc*. 1987;114:213-215.
69. Dietschi D, Magne P, Holz J. Recent trends in esthetic restorations for posterior teeth. *Quintessence Int*. 1994;25:659-677.
70. Jørgensen KD, Hisamitsu H. Class 2 composite restorations: prevention in vitro of contraction gaps. *J Dent Res*. 1984;63:141-145.
71. Ericson D, Dérand T. Reduction of cervical gaps in class II composite resin restorations. *J Prosthet Dent*. 1991;65:33-37.
72. Bowen RL, Setz LE. Posterior composite restorations with novel structure [abstract 642]. *J Dent Res*. 1986;65:797.
73. Spreafico R. Direct resin composite restorations in posterior teeth. In: DeGrange M, Roulet JF, eds. *Minimally Invasive Restorations with Bonding*. Chicago, Ill: Quintessence Publishing; 1997:103.
74. Krejci I, Lutz F, Krejci D. The influence of different base materials on marginal adaptation and wear of conventional Class II composite resin restorations. *Quintessence Int*. 1988;19:191-198.
75. Neo JC, Denehy GE, Boyer DB. Effects of polymerization techniques on uniformity of cure of large-diameter, photo-initiated composite resin restorations. *J Am Dent Assoc*. 1986;113:905-909.
76. Dietschi D, Scampa U, Campanile G, et al. Marginal adaptation and seal of direct and indirect Class II composite resin restorations: an in vitro evaluation. *Quintessence Int*. 1995;26:127-138.
77. Liebenberg WH. Successive cusp build-up: an improved placement technique for posterior direct resin restorations. *J Can Dent Assoc*. 1996;62:501-507.
78. Eccles JD. Tooth surface loss from abrasion, attrition and erosion. *Dent Update*. 1982;9:373-381.
79. Grippo JO. Noncarious cervical lesions: the decision to ignore or restore. *J Esthet Dent*. 1992;4(suppl):55-64.
80. Lambrechts P, Van Meerbeek B, Perdigão J, et al. Restorative therapy for erosive lesions. *Eur J Oral Sci*. 1996;104:229-240.
81. Davies SJ, Gray RJ, Qualtrough AJ. Management of tooth surface loss. *Br Dent J*. 2002;192:11-23.
82. Fahl N Jr, Denehy GE, Jackson RD. Protocol for predictable restoration of anterior teeth with composite resins. *Pract Periodontics Aesthet Dent*. 1995;7:13-21.
83. Winter R. Visualizing the natural dentition. *J Esthet Dent*. 1993;5:102-117.
84. Seluk LW, LaLonde TD. Esthetics and communication with a custom shade guide. *Dent Clin North Am*. 1985;29:741-751.
85. Pink FE, Frazier KB. Evaluation of a custom shade guide. *Gen Dent*. 1990;38:186-188.
86. Pizzamiglio E. A color selection technique. *J Prosthet Dent*. 1991;66:592-596.
87. Croll TP. Alternative methods for use of the rubber dam. *Quintessence Int*. 1985;16:387-392.
88. Liebenberg WH. General field isolation and the cementation of indirect restorations: Part I. *J Dent Assoc S Afr*. 1994;49:349-353.
89. Anttonen V, Seppä L, Hausen H. Clinical study of the use of the laser fluorescence device DIAGNOdent for detection of occlusal caries in children. *Caries Res*. 2003;37:17-23.
90. Pretty IA, Smith PW, Edgar WM, et al. Detection of in vitro demineralization adjacent to restorations using quantitative light induced fluorescence (QLF). *Dent Mater*. 2003;19:368-374.
91. Leinfelder KF. Using composite resin as a posterior restorative material. *J Am Dent Assoc*. 1991;122:65-70.
92. Kanca J III. Improving bond strength through acid etching of dentin and bonding to wet dentin surfaces. *J Am Dent Assoc*. 1992;123:35-43

93. Nakabayashi N, Nakamura M, Yasuda N. Hybrid layer as a dentin-bonding mechanism. *J Esthet Dent*. 1991;3:133-138.
94. Kanca J III. Resin bonding to wet substrate. II. Bonding to enamel. *Quintessence Int*. 1992;23:625-627.
95. Dennison JB, Yaman P, Seir R, et al. Effect of variable light intensity on composite shrinkage. *J Prosthet Dent*. 2000;84:499-505.
96. Reinhardt KJ. Effect of the light source on the marginal adaptation of composite fillings [in German]. *Dtsch Zahnarztl Z*. 1991;46:132-134.
97. Goracci G, Mori G, de Marlins C. Polymerizatione di materiali compositi. *Dent Cadmos*. 1993;7:50-62.
98. Rees JS, Jacobsen PH. Restoration of posterior teeth with composite resin. 1: Direct-placement composite. *Dent Update*. 1996;23:406-410.
99. Eakle WS, Ito RK. Effect of insertion technique on microleakage in mesio-occlusodistal composite resin restorations. *Quintessence Int*. 1990;21:369-374.
100. Duke ES. Direct posterior composites. *J Indiana Dent Assoc*. 1993;72:35-39.
101. Wieczkowski G Jr, Joynt RB, Klockowski R, et al. Effects of incremental versus bulk fill technique on resistance to cuspal fracture of teeth restored with posterior composites. *J Prosthet Dent*. 1988;60:283-287.
102. Hansen EK. Effect of cavity depth and application technique on marginal adaptation of resins in dentin cavities. *J Dent Res*. 1986;65:1319-1321.
103. Jefferies SR, Barkmeier WW, Gwinnett AJ. Three composite finishing systems: a multisite in vitro evaluation. *J Esthet Dent*. 1992;4:181-185.
104. Goldstein RE. Finishing of composites and laminates. *Dent Clin North Am*. 1989;33:305-318.
105. Strassler HE, Bauman G. Current concepts in polishing composite resins. *Pract Periodontics Aesthet Dent*. 1993;5(3 suppl 1):12-17.
106. Chan KC, Fuller JL, Hormati AA. The ability of foods to stain two composite resins. *J Prosthet Dent*. 1980;43:542-545.
107. Gedik R, Hürmüzlü F, Co kun A, et al. Surfaceroughness of new micro-hybrid resin-based composites. *J Am Dent Assoc*. 2005;136:1106-1112.
108. Dickinson GL, Leinfelder KF. Assessing the long-term effect of a surface penetrating sealant. *J Am Dent Assoc*. 1993;124:68-72.
109. Terry DA, McGuire MK, McLaren E, et al. Perioesthetic approach to the diagnosis and treatment of carious and noncarious cervical lesions: Part I. *J Esthet Restor Dent*. 2003;15:217-232.
110. Liebenberg WH. Extending the use of rubber dam isolation: alternative procedures. Part I. *Quintessence Int*. 1992;23:657-665.
111. Terry DA, Leinfelder KF, Geller W. *Aesthetic & Restorative Dentistry: Material Selection & Technique*. Stillwater, MN: Everest Publishing Media; 2009.
112. Perdigão J, Geraldeli S. Bonding characteristics of self-etching adhesives to intact versus prepared enamel. *J Esthet Restor Dent*. 2003;15:32-42.
113. Craig RG. Review of dental impression materials. *Adv Dent Res*. 1988;2:51-64.

POST EXAMINATION INFORMATION

To receive continuing education credit for participation in this educational activity you must complete the program post examination and receive a score of 70% or better.

Traditional Completion Option:

You may fax or mail your answers with payment to Dentistry Today (see Traditional Completion Information on following page). All information requested must be provided in order to process the program for credit. Be sure to complete your "Payment", "Personal Certification Information", "Answers" and "Evaluation" forms, Your exam will be graded within 72 hours of receipt. Upon successful completion of the post-exam (70% or higher), a "letter of completion" will be mailed to the address provided.

Online Completion Option:

Use this page to review the questions and mark your answers. Return to dentalCEtoday.com and signin. If you have not previously purchased the program select it from the "Online Courses" listing and complete the online purchase process. Once purchased the program will be added to your User History page where a Take Exam link will be provided directly across from the program title. Select the Take Exam link, complete all the program questions and Submit your answers. An immediate grade report will be provided. Upon receiving a passing grade complete the online evaluation form. Upon submitting the form your Letter Of Completion will be provided immediately for printing.

General Program Information:

Online users may login to dentalCEtoday.com anytime in the future to access previously purchased programs and view or print "letters of completion" and results.

POST EXAMINATION QUESTIONS

1. **A successful restorative procedure for posterior composite resins relies on which of the following elements?**
   a. Adhesion.
   b. Clinical technique.
   c. Restorative material selection.
   d. All of the above.

2. **In a restorative technique using composite resins, the polymerization reaction of the resin matrix phase could compromise dimensional stability. Therefore, a comprehensive understanding of the complex interplay between color and adhesion is necessary.**
   a. The first statement is correct and the second is incorrect.
   b. Both statements are correct.
   c. Both statements are incorrect.
   d. The first statement is incorrect and the second statement is correct.

3. **Polymerization shrinkage or curing contraction is the amount of volumetric increase a composite system undergoes because of the curing process. The cross-linking of resin monomers into polymers is responsible for an unconstrained volumetric shrinkage of 2% to 8%.**
   a. The first statement is correct and the second is incorrect.
   b. Both statements are correct.
   c. Both statements are incorrect.
   d. The first statement is incorrect and the second statement is correct.

4. **Factors that influence polymerization shrinkage include which of the following?**
   a. Filler content of the composite.
   b. Cavity configuration.
   c. Water sorption.
   d. all of the above.

5. **Repeated flexural forces from functional loads after placement of a cervical composite restoration can cause adhesive failure at the dentin-resin interface, which can result in which of the following?**
   a. Microleakage.
   b. Partial or complete debonding of the restoration.
   c. A and B.
   d. None of the above.

6. **Optimizing the adhesion of restorative biomaterials to the mineralized hard tissues of the tooth can enhance the following:**
   a Marginal adaptation and seal.
   b. Reliability and longevity of the adhesive restoration.
   c. Mechanical strength.
   d. All of the above.

7. **The word "adhesion" is derived from the Latin roots that translate as "to" and "stick together." The adherend is the material or initial substrate to which the adhesive is applied.**
   a. The first statement is correct and the second is incorrect.
   b. Both statements are correct.
   c. Both statements are incorrect.
   d. The first statement is incorrect and the second statement is correct.

8. **Inherent in the formation of an optimal adhesive bond is the ability of the adhesive to wet and spread on the adherends being joined. Good wetting usually occurs with solids that demonstrate low surface energy.**
   a. The first statement is correct and the second is incorrect.
   b. Both statements are correct.
   c. Both statements are incorrect.
   d. The first statement is incorrect and the second statement is correct.

9. **The bonded restorative complex includes which of the following?**
   a. Adhesive layer.
   b. Restorative material.
   c. Outer layers of the substrate.
   d. All of the above.

10. **The integrity of the adhesive bonded interface is subject to failure arising from defects which can be the result of which of the following?**
    a. Trapped air voids.
    b. Areas of interfacial contamination.
    c. Bubbles within the adhesive.
    d. All of the above.

11. **A restorative material properly joined to the tooth substrate is able to provide the following:**
    a. Restoration retention.
    b. Reduction of stress at the tooth-restorative interface.
    c. Biomechanical reinforcement of tooth structure.
    d. All of the above.

12. **A durable interfacial adhesion between the tooth and biomaterial requires which of the following?**
    a. A low contact angle.
    b. Voids formed from solvent evaporation.
    c. A clean surface of the substrate.
    d. A and C.

13. **Incremental layering techniques of composite resin can provide which of the following?**
    a. Densification and improved marginal adaptation.
    b. Thorough polymerization of the restorative material.
    c. A and B.
    d. None of the above.

14. **The factors that influence the margin quality and strength of a composite restoration include:**
    a. Viscosity and stiffness of the composite resin.
    b. Finishing and polishing techniques.
    c. Polymerization shrinkage and restorative application techniques.
    d. All of the above.

15. **Shade selection should be accomplished prior to dental dam placement to prevent improper color matching as a result of dehydration and elevated values. When teeth dehydrate, water replaces the air between the enamel rods, changing the refractive index, which makes the enamel appear translucent.**
    a. The first statement is correct and the second is incorrect.
    b. Both statements are correct.
    c. Both statements are incorrect.
    d. The first statement is incorrect and the second statement is correct.

16. **A smooth restorative surface and/or restorative-tooth interface provides which of the following?**
    a. Minimizes the potential for gingival inflammation.
    b. Reduces the potential for surface staining and secondary caries.
    c. Increases plaque retention.
    d. A and B.

Achieving Excellence Using an Advanced Biomaterial: Part 2

PROGRAM COMPLETION INFORMATION

If you wish to purchase and complete this activity traditionally (mail or fax) rather than Online, you must provide the information requested below. Please be sure to select your answers carefully and complete the evaluation information. To receive credit you must answer at least six of the eight questions correctly.

Complete online at: ***www.dentalcetoday.com***

TRADITIONAL COMPLETION INFORMATION:

Mail or Fax this completed form with payment to:

Dentistry Today
Department of Continuing Education
100 Passaic Avenue
Fairfield, NJ 07004
Fax: 973-882-3662

PAYMENT & CREDIT INFORMATION:

Examination Fee: $40.00 **Credit Hours:** 2.0

Note: There is a $10 surcharge to process a check drawn on any bank other than a US bank. Should you have additional questions, please contact us at (973) 882-4700.

❑ I have enclosed a check or money order.

❑ I am using a credit card.

My Credit Card information is provided below.

❑ American Express ❑ Visa ❑ MC ❑ Discover

Please provide the following (please print clearly):

Exact Name on Credit Card

Credit Card # Expiration Date /

Signature

ADA C·E·R·P® Continuing Education Recognition Program
Dentistry Today is an ADA CERP Recognized Provider.

Academy of General Dentistry PACE Program Approval for Continuing Education

Approved PACE Program Provider FAGD/MAGD Credit Approval does not imply acceptance by a state or provincial board of dentistry or AGD endorsement. June 1, 2009 to May 31, 2011 AGD Pace approval number: 309062

PERSONAL CERTIFICATION INFORMATION:

Last Name (PLEASE PRINT CLEARLY OR TYPE)

First Name

Profession / Credentials License Number

Street Address

Suite or Apartment Number

City State Zip Code

Daytime Telephone Number With Area Code

Fax Number With Area Code

E-mail Address

ANSWER FORM: COURSE #: 119

Please check the correct box for each question below.

1.	❑ a	❑ b	❑ c	❑ d	9.	❑ a	❑ b	❑ c	❑ d
2.	❑ a	❑ b	❑ c	❑ d	10.	❑ a	❑ b	❑ c	❑ d
3.	❑ a	❑ b	❑ c	❑ d	11.	❑ a	❑ b	❑ c	❑ d
4.	❑ a	❑ b	❑ c	❑ d	12.	❑ a	❑ b	❑ c	❑ d
5.	❑ a	❑ b	❑ c	❑ d	13.	❑ a	❑ b	❑ c	❑ d
6.	❑ a	❑ b	❑ c	❑ d	14.	❑ a	❑ b	❑ c	❑ d
7.	❑ a	❑ b	❑ c	❑ d	15.	❑ a	❑ b	❑ c	❑ d
8.	❑ a	❑ b	❑ c	❑ d	16.	❑ a	❑ b	❑ c	❑ d

PROGRAM EVAUATION FORM

Please complete the following activity evaluation questions.

Rating Scale: Excellent = 5 and Poor = 0

Course objectives were achieved. _____

Content was useful and benefited your clinical practice. _____

Review questions were clear and relevant to the editorial. _____

Illustrations and photographs were clear and relevant. _____

Written presentation was informative and concise. _____

How much time did you spend reading the activity & completing the test? _____